

NC GROUT

NON-CORROSIVE NON-SHRINK CEMENTITIOUS GROUT

DESCRIPTION

NC GROUT is a non-shrink, non-staining grout. Its multi-flow quality allows this product to be used at various consistencies including pumping into inaccessible areas. NC GROUT may be packed, rodded, vibrated, poured or pumped. It has high compressive and flexural strengths and is non-rusting and non-corrosive. For high performance base plate applications, use NS GROUT.

PRIMARY APPLICATIONS

- Interior or exterior
- Columns
- Precast structural members
- Machinery base plates
- Post tensioned cables
- Tee joints
- Structural steel
- Anchor bolts

FEATURES/BENEFITS

- Extended working time for easier placement
- Sets rapidly and uniformly
- Can be used in wet areas - will not rust
- Versatile flow capability
- Above or below grade
- Can contribute to LEED points

TECHNICAL INFORMATION

PROPERTY	PLASTIC CONSISTENCY	POURABLE CONSISTENCY	FLUID CONSISTENCY
	0.9 GAL/50 LB (3.4 L/22.7 KG)	1.0 GAL/50 LB (3.8 L/22.7 KG)	1.2 GAL/50 LB (4.5 L/22.7 KG)
Flow Rate (ASTM C 230)	100% (Flow Table)	120% (Flow Table)	30 seconds (flow cone)
Compressive Strength (ASTM C109 Modified*) 2 in (50 mm) cubes	3 days 5500 psi (38 MPa) 7 days 7500 psi (52 MPa) 28 days 8000 psi (55 MPa)	3 days 4000 psi (28 MPa) 7 days 6000 psi (41 MPa) 28 days 7500 psi (52 MPa)	3 days 3000 psi (21 MPa) 7 days 4800 psi (33 MPa) 28 days 6000 psi (41 MPa)
Expansion (CRD C 621)	3 days 0.06% 28 days 0.08%	3 days 0.08% 28 days 0.08%	3 days 0.09% 28 days 0.10%
Setting Time (ASTM C 191)	Initial: 1.5 to 2 hrs Final: 3 to 4 hrs	Initial: 2.5 to 3.5 hrs Final: 4 to 5 hrs	Initial: 5 to 5.5 hrs Final: 7 to 8 hrs
Flexural Strength (ASTM C 348)	7 day: 900 psi (6 MPa) 28 day: 1200 psi (8 MPa)	--	--
Modulus of Elasticity (ASTM C 469)	4.31 x 10 ⁶ psi (3.0 x 10 ⁴ MPa)	--	--

*See ASTM C 1107 Section 11.5

Note: Normal 28 day compressive strength of portland cement concrete is 3,000 psi. Controlled expansion measures the grout's ability to attain and maintain positive and complete contact with base plates, rebars, bolts, etc. Fluidity and flowability describes the grout's ability to flow freely into a cavity. Pull-out tests are conducted to establish anchoring strength. There are no standard tests for this. NC GROUT was tested by drilling 2" (50mm) diameter holes in fully cured concrete with a compressive strength of 7,520 psi (52 MPa). Pull out tests made at 7, 14 and 28 days on #9 grade 60 bars embedded in the holes at depths of 12" (200mm), 15" (380mm), and 18" (460 mm) showed that the ultimate failure load exceeded the 60,000 psi (414 MPa) specified minimum yield point of the rebar.

PACKAGING

NC GROUT is packaged in 50 lb (22.7 kg) poly-lined bags.

SHELF LIFE

2 years in original, unopened package



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110
Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596
www.euclidchemical.com

An **RPM** Company



SPECIFICATIONS/COMPLIANCES

- Corp of Engineer Specifications CRD C 621 and CRD C 588
- ASTM standards: ASTM C 827 and ASTM C 1107

COVERAGE

One 50 lb (22.7 kg) bag will yield approximately 0.43 ft³ (0.012 m³) of grout.

DIRECTIONS FOR USE

Surface Preparation: Concrete surface must be structurally sound, dry, free of grease, oils, coatings, dust, curing compounds and other contaminants. Edges of concrete to be grouted that are less than 1" (25 mm) thick must be vertically cut to form a uniform edge. Smooth substrates must be abraded to ensure proper bonding. Shim and anchor support elements to prevent movement. Steel must be free of oils, greases, dirt, old coatings or chemical contaminants. Saturate the prepared area with potable water for 12 to 24 hours before application. Remove excess water from holes and voids just before placement to prevent dilution of the grout. **Mixing:** NC GROUT is factory-proportioned and comes ready to use by adding only potable water. Use 0.9 gal (3.4L) of water per bag of grout for a plastic mix: 1 gal (3.8L) for a pourable mix and 1.2 gal (4.5L) for a high flow mix. For a uniform mix, use a paddle type mortar mixer. Add 2/3 of the water for the mix consistency desired into the mixer. Add the grout and mix partially. Add the remaining water to achieve the final consistency. Thoroughly mix the entire quantity for 2 to 3 minutes. Do not mix more material than can be placed in 30 minutes. **Application:** All grouting should be done using established procedures and recommendations of ACI for placing and curing concrete. The method of forming must provide for rapid continuous pouring of the grout and allow a clearance of at least 3" (76mm) for entry and a "grout head" of 4" to 6" (100 to 152 mm). Avoid air entrapment by providing adequate venting at the high point and by pouring the grout from one side only. Forms should be 1 to 2" (25 to 50 mm) above the base plate. NC GROUT must be placed by pumping, pouring, rodding or vibrating. Lengths of small link chain laid in the form before placing the grout will assist in compacting the grout and eliminating air voids. The grout must be placed and compacted within 30 minutes after mixing. In applications where grout thickness exceeds 5" (12.7cm) up to 25 lbs(11.3 kg) of 3/8" (9.5 mm) clean and damp pea gravel may be added per 50 lb (22.7 kg) bag to extend the mix. After placement, rapid drying must be prevented by covering the grout with wet burlap or by applying a membrane forming curing compound from the Euclid Chemical series of products. The forms may be removed after the grout has hardened to an initial set (see material properties). When grouting at higher temperatures, use cold water, shade the area to be grouted and protect the placed grout from direct sunlight for at least 48 hours by covering with wet burlap. When grouting at low temperatures, raise the temperature of foundation bedplate by using steam or infrared heaters. Use warm mixing water and cover the grout to retain warmth. Do not apply heat directly to the grout after its placement. Chloride based set accelerators are not recommended.

CLEAN-UP

Clean tools and equipment with water immediately following. Clean drips with water while still wet. Dried NC GROUT will require mechanical abrasion for removal.

PRECAUTIONS/LIMITATIONS

- Do not add anything but potable water.
- Do not add water in an amount that will cause bleeding or segregation. More or less water may be required to achieve a 25 second flow or the desired placing consistency, depending on temperature and other variables.
- Do not retemper with additional water after the mixture has started to set.
- Do not add admixtures or fluidifiers.
- Do not add sand or cement to the grout since this action will change its precision grouting characteristics.
- Do not aerate the mix.
- Use appropriate cold and hot weather grouting procedures per ACI guidelines as the temperature dictates.
- Proper curing practices must be used.
- Apply at temperatures 40°F (4°C) and rising.
- Do not use as an overlay.
- In all cases, consult the Material Safety Data Sheet before use.

Rev. 05.11

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.